



ELSEVIER

9 December 1996

PHYSICS LETTERS A

Physics Letters A 223 (1996) 308–312

## Crystal field and spectrum of $\text{Pr}^{4+}$ in $\text{BaPrO}_3$

M.N. Popova<sup>a,1</sup>, S.A. Klimin<sup>a</sup>, B.Z. Malkin<sup>b</sup>, L.A. Kasatkina<sup>b</sup>, G. Cao<sup>c</sup>, J. Crow<sup>c</sup><sup>a</sup> *Institute of Spectroscopy, Russian Academy of Sciences, 142092 Troitsk, Moscow Region, Russian Federation*<sup>b</sup> *Kazan State University, 420008 Kazan, Russian Federation*<sup>c</sup> *National High Magnetic Field Laboratory, Florida State University, Tallahassee, FL 32306, USA*

Received 31 August 1996; accepted for publication 20 September 1996

Communicated by V.M. Agranovich

### Abstract

We have measured the absorption spectrum of  $\text{BaPrO}_3$  in the spectral range 1900–11000  $\text{cm}^{-1}$ . All the energy levels of the 4f electronic configuration of the  $\text{Pr}^{4+}$  ion in a crystal have been observed for the first time. We describe the total set of electron-nuclear states and the integral intensities of the magnetic dipole transitions of the  $\text{Pr}^{4+}$  in  $\text{BaPrO}_3$  in the framework of the crystal field approximation. The crystal field parameters corresponding to the real orthorhombic symmetry of  $\text{BaPrO}_3$  are obtained with the exchange charge model.

PACS: 78.20.Dj; 71.70.Ej

Keywords: Tetravalent praseodymium

### 1. Introduction

One of the most challenging problems in the modern physics of lanthanide and actinide compounds is the mechanism of the strong superexchange interaction which gives rise to a long-range magnetic ordering at relatively high temperatures in different oxides, in particular, containing tetravalent f-ions [1]. To treat this problem one needs a detailed knowledge of the f-electron energy levels in the crystal field. Among the lanthanides, only cerium, praseodymium and terbium can be obtained in the tetravalent state, and the case of the  $\text{Pr}^{4+}$  ion, with only one electron in the 4f shell, is the most promising for experimental and theoretical studies.

The first observation of the optical spectrum of  $\text{Pr}^{4+}$  in crystals, namely in  $\text{BaPrO}_3$ , was reported in

Ref. [2]. In this orthorhombically distorted perovskite (space group  $\text{Pbnm}$ ) praseodymium is tetravalent by valence arguments. The  $\text{Pr}^{4+}$  ions have an almost octahedral arrangement of six near-neighbour oxygen ions [3]. Deformations and mutual rotations of these octahedra result in a drop of the point symmetry of the fourfold  $4b$  position for  $\text{Pr}^{4+}$  ion in the lattice from  $\text{O}_h$  to  $\text{C}_i$ , but a consideration of the spectral and magnetic properties with a reference to the cubic symmetry has been useful as a first approximation [1,2,4]. The  $\Gamma_7$  ground Kramers doublet and four excited levels ( $\Gamma_8$ ,  $\Gamma'_7$ ,  $\Gamma'_8$  and  $\Gamma_6$  in the order of growing energies) result from the  $4f^1$  electron configuration of  $\text{Pr}^{4+}$  in the crystal field of  $\text{O}_h$  symmetry. The quadruplet ( $\Gamma_8$  and  $\Gamma'_8$ ) levels split into two Kramers doublets for a crystal field of lower symmetry. Only magnetic dipole optical transitions are allowed, the  $\Gamma_7 \rightarrow \Gamma_6$  transition being forbidden.

<sup>1</sup> E-mail: [popova@isan.msk.su](mailto:popova@isan.msk.su).